

# UCT Coatings Plating Options

Plating Option	Corrosion Protection	Wear Resistance	Hardness Level	Heat Treatment
<b>EXO</b>	Enhanced	Excellent	82 HRC	725°F @ 1.5 hrs <u>or</u> 485°F @ 5 hrs
<b>EXO-H</b>	Enhanced	Excellent	82 HRC	725°F @ 1.5 hrs <u>or</u> 485°F @ 5 hrs
<b>EXO-NH</b>	Good	Good	68 HRC	None
<b>EXO-CR</b>	Good	Excellent	82 HRC	725°F @ 1.5 hrs <u>or</u> 485°F @ 5 hrs
<b>EXO-CR+</b>	Excellent	Good	68 HRC	None
<b>EXO-CRX</b>	Superior	Good	68 HRC	None

